

Effects of Orbital Degeneracy and Electron Correlation on Charge Dynamics in Perovskite Manganese Oxides

Hiroki NAKANO, Yukitoshi MOTOME¹ and Masatoshi IMADA

Institute for Solid State Physics, University of Tokyo, Roppongi 7-22-1, Minato-ku, Tokyo 106-8666

¹*Department of Physics, Tokyo Institute of Technology, Oh-okayama 2-12-1, Meguro-ku, Tokyo 152-8551*

(Received)

Taking the orbital degeneracy of e_g conduction bands and the Coulomb interaction into account in a double-exchange model, we investigate charge dynamics of perovskite Mn oxides by the Lancz s diagonalization method. In the metallic phase near the Mott insulator, it is found that the optical conductivity for a spin-polarized two-dimensional system exhibits a weight transfer to a broad and incoherent structure within the lower-Hubbard band together with a suppressed Drude weight. It reproduces qualitative feature of the experimental results. As an orbital effect, we find that an anomalous charge correlation at quarter filling suppresses the coherent charge dynamics and signals precursor to the charge ordering.

KEYWORDS: perovskite manganites, double-exchange model, Coulomb interaction, orbital degeneracy, metal-insulator transition, ferromagnetic metal, optical conductivity, Drude weight, incoherent charge dynamics, charge ordering, exact diagonalization, strongly correlated electron system

Although properties of perovskite manganese oxides $R_{1-x}A_x\text{MnO}_3$ (R =rare earth, A =Ca, Sr, Ba or Pb) showing colossal magnetoresistance¹⁾ are to some extent reproduced by a double-exchange (DE) model composed of non-interacting (NI) electrons in a non-degenerate e_g conduction band ferromagnetically coupled with t_{2g} localized spins of $S=3/2$,^{2,3,4,5,6)} there remain open problems which cannot be understood within the framework of this model. One of them is that $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$ in the ferromagnetic and metallic phase near the insulator ($x=0.175$) shows a large and broad structure of incoherence in the optical response together with a relatively small Drude weight at low temperatures^{7,8)} though the spin degrees of freedom cannot contribute to the incoherence under the perfect polarization of spins. Some other degrees of freedom not contained in the DE model must be involved. Possible origins of the incoherence are the dynamical Jahn-Teller (JT) distortion,⁹⁾ e_g orbital degeneracy^{10,11,12)} and electronic correlations.^{13,14)} In ref. 9 employing the dynamical mean-field approximation, the electronic correlations are not taken into account though they are not negligible and play an essential role as shown later. In this work, we focus on the latter two and make it clear how large incoherence is induced in a minimal model of these two origins.

On this subject, related studies have already been done under some approximations. Shiba, Shiina and Takahashi claimed that the large incoherence in the optical absorption originates in the degeneracy of the e_g orbitals,¹⁰⁾ although the Mott insulator in the undoped system is not reproduced because the strong correlation effect is not seriously considered.^{10,11,12)} Ishihara, Yamanaka and Nagaosa derived an effective t - J type Hamiltonian considering the degeneracy of the e_g orbitals and the strong interaction.¹³⁾ They obtained incoherent part of the optical conductivity in a mean-field treatment. In

such a mean-field treatment, unfortunately, the Drude weight is absent with a diverging specific heat coefficient γ in contrast to the experimental results.¹⁵⁾ Horsch *et al.* applied a finite-temperature Lancz s method to the ‘orbital’ t - J model.¹⁴⁾ In their method, however, the accessible temperature range is much higher than the experimental conditions.¹⁶⁾ Consequently their Drude weight is largely suppressed simply by thermal fluctuations, which makes hard to compare with the experimental results. In order to discuss this metal-insulator transition, fluctuation effects are important; a reliable way to calculate beyond biased approximations is required.

In this work, we examine the Hamiltonian given by

$$\mathcal{H} = \sum_{ij} \sum_{\nu\nu'} t_{ij}^{\nu\nu'} c_{i\nu}^\dagger c_{j\nu'} + U \sum_i (n_{i1} - \frac{1}{2})(n_{i2} - \frac{1}{2}), \quad (1)$$

as a minimal model mentioned above. This model is derived from the generalized DE model with e_g -orbital degeneracy under the assumptions of strong Hund’s-rule coupling and perfect spin polarization.¹⁷⁾ Here $t_{ij}^{\nu\nu'}$ denotes the hopping integral and U is the effective interorbital Coulomb interaction obtained after subtracting the Hund’s-rule coupling energy between e_g electrons. The orbitals $d_{x^2-y^2}$ and $d_{3z^2-r^2}$ correspond to $\nu=1$ and $\nu=2$, respectively. Note that this model is essentially different from the usual Hubbard model. Actually, the difference appears even in the NI case as shown later. We consider here only the nearest-neighbor hopping given by $t_{ij}^{11} = -3/4t_0$, $t_{ij}^{22} = -1/4t_0$, $t_{ij}^{12} = t_{ij}^{21} = -(+)\sqrt{3}/4t_0$ along $x(y)$ -direction in two dimensions. Here, we investigate the two-dimensional (2D) model given by eq. (1) based on the following reasons. One is that the three-dimensional (3D) system of $R_{1-x}A_x\text{MnO}_3$ keeps a perfectly spin-polarized plane not only in the ferromagnetic doped phase but also in the A -type antiferromagnetic insulating phase at $x=0$ so that the spin polarization is retained in a 2D plane over all regions of interest. The

second is that a similar incoherent feature in the optical conductivity was also reported in the 2D system, for instance, in $\text{La}_{1.2}\text{Sr}_{1.8}\text{Mn}_2\text{O}_7$.¹⁸⁾ It is therefore likely that the 2D system can capture basic physics of the incoherent charge dynamics. The model (1) contains an implicit variable parameter of a doping concentration $\delta \equiv 1 - \frac{N_e}{N_s}$ or an electron density $n \equiv \frac{N_e}{N_s}$, where N_e and N_s denote the numbers of electrons and sites, respectively. Recently, this model (1) has been studied by means of quantum Monte Carlo (QMC) method.^{17, 19, 20)} There, the relation was discussed between the incoherence of the charge dynamics and divergences of both a staggered orbital correlation length and the compressibility as $\delta \rightarrow 0$. To get more insight, it is desired to calculate quantities directly connected to the charge dynamics. In this paper, then, we discuss effects of the orbital degeneracy and the electronic correlation based on direct calculations of dynamical quantities about charge transport.

We here employ, as another unbiased method, exact diagonalization of finite-size (FS) clusters, using the Lancz s algorithm and the continued-fraction-expansion method²¹⁾ to obtain dynamical quantities at zero temperature. The sizes of the cluster calculated in this work are $\sqrt{10} \times \sqrt{10}$ and 4×4 . In the $\sqrt{10} \times \sqrt{10}$ -site system, to reduce the FS effect,²²⁾ we introduce the Aharonov-Bohm flux Φ in the hopping term as the twisted boundary condition and find the optimized boundary so as to minimize the ground-state energy. In the 4×4 system, we choose the boundary condition among the periodic ($\Phi = (0, 0)$), the anti-periodic ($\Phi = (\pi, \pi)$) and the mixed ($\Phi = (0, \pi)$ or $(\pi, 0)$) ones.

We here calculate the optical conductivity defined as $\sigma(\omega) = [\sigma_x(\omega) + \sigma_y(\omega)]/2$ where $\sigma_\alpha(\omega) = 2\pi e^2 D_\alpha \delta(\omega) + \frac{\pi e^2}{N} \sum_{m \neq 0} \frac{|\langle m | j_\alpha | 0 \rangle|^2}{E_m - E_0} \delta(\omega - E_m + E_0)$. Here, D_α is the Drude weight; j_α is a current operator along α -direction ($\alpha = x, y$) given by $j_\alpha = -i \sum_{i, i+\delta_\alpha} t_{i, i+\delta_\alpha}^{\nu\nu'} (c_{i\nu}^\dagger c_{i+\delta_\alpha, \nu'} - c_{i+\delta_\alpha, \nu'}^\dagger c_{i\nu})$; and $|m\rangle$ denotes an eigenstate of the system with the energy eigenvalue of E_m . Note that $m = 0$ represents the ground state. The averaging operation is performed to reduce the FS effect and to cancel the anisotropy due to the anisotropic boundary condition. The sum rule $\int_0^\infty \sigma(\omega) d\omega = \pi e^2 K$ is satisfied, where $-4K$ is the kinetic energy per site. We will call K the total weight hereafter. When U is large enough, we also calculate the effective carrier density defined as $N_{\text{eff}} = \frac{1}{\pi e^2} \int_0^{\omega_c} \sigma(\omega) d\omega$ where ω_c is a frequency just below the bottom edge of the upper-Hubbard (UH) band. In this work, we make a further procedure to reduce FS effects. The procedure is a multiplication of a correction factor determined from the FS effects in the NI cases. The factor is defined by $r = K_{\infty}^{(U=0)}/K_{N_s}^{(U=0)}$, where $K_{\infty}^{(U=0)}$ and $K_{N_s}^{(U=0)}$ are the total weights in the thermodynamic limit and in the N_s -site case when $U=0$, respectively. Hereafter, all the quantities obtained after this procedure are labeled with suffix c, for example, D^c . This procedure successfully reduces the FS effects in the usual Hubbard model in one and two dimensions.²²⁾ Here, we take a large value of $U/t_0=16$, at which a large Hubbard gap opens at half filling and the FS effect is expected to be less serious.

We first show our results of the doping dependence of the total weights, the effective carrier densities and the Drude weights in Fig. 1. Even in the NI case, as was reported in the 3D model in ref. 10, the present model (1) in 2D exhibits a different doping dependence between the Drude weight and the total weight due to the hopping between the $d_{x^2-y^2}$ and $d_{3z^2-r^2}$ bands. (See the gray curves in Fig. 1.) However, the Drude weight remains finite even at half filling, which indicates that the system is metallic in this NI case. When $U/t_0 = 16$, on the other hand, the Drude weight at half filling has a very small value ~ 0.0005 in the case of $\sqrt{10} \times \sqrt{10}$ -site system. This small value indicates that the system is Mott insulating and that even a cluster of $\sqrt{10} \times \sqrt{10}$ sites can reproduce well the bulk quantities. In the dilute-electron-density region ($\delta \sim 1$), the total weights, the effective carrier density and the Drude weights for $U/t_0 = 16$ behave close to the corresponding quantities for the NI case, which indicates that effects of Coulomb interaction are small in this region. At $\delta = 0.5$, the Drude weight shows a significant dip, which reminds us of a charge ordering with a CE -type magnetic structure observed in such materials as $\text{Nd}_{0.5}\text{Sr}_{0.5}\text{MnO}_3$ ²⁵⁾ and $\text{Pr}_{0.5}\text{Ca}_{0.5}\text{MnO}_3$.^{26, 27)} Although the value of the Drude weight is still finite, this dip is neither seen in the NI case of the present model nor in the usual Hubbard model with finite U .²²⁾ We will discuss this issue later. With decreasing δ further, the Drude weight and the effective carrier density vanish for $U/t_0=16$ while the two quantities increase for $U=0$. It should be emphasized here that the overall behaviors of the Drude weight and the effective carrier density except for the dip at $\delta=0.5$ in the Drude weight are qualitatively similar to the ones of the usual Hubbard model in 2D.²²⁾ We, however, also note that the critical region of suppressed Drude weight near $\delta=0$ seems to be narrower than that in the 2D Hubbard model due to the imbalanced populations of electrons in $d_{x^2-y^2}$ and $d_{3z^2-r^2}$.

In Fig. 2, we present results for the incoherent part of $\sigma(\omega)$. One can see in Fig. 2 (a) that, at half filling, a large gap exists and that only the weight transfer across the gap to the UH band appears. As shown in Figs. 2 (b) and (c), the more holes from half filling are doped, the more weights are transferred from the region above the gap to the region within the lower-Hubbard (LH) band. Especially, note that weights for $U/t_0=16$ spread in a wider region than those in the NI case shown in the inset of Fig. 2(b). The QMC study shows a critical enhancement of the orbital correlation length induced by U which would cause the incoherence of the charge dynamics.¹⁷⁾ The orbital correlation in the present calculation is in agreement with that in the QMC. The present calculations indeed show a close relation between the orbital fluctuation and the mid-gap incoherence. The qualitative feature of the incoherent charge response experimentally observed in $\sigma(\omega)$ is reproduced in the present calculation, which supports the importance of combined effects from orbital degeneracy and strong correlations. On a quantitative level, however, $D/K \sim 0.51$ at $\delta \sim 0.125$ in the present result is still larger than the experimental indications, ~ 0.2 .

To understand the dip at $\delta = 0.5$ in Fig. 1, let us dis-

cuss the orbital and charge structures in the ground state at $\delta = 0.5$.²³⁾ The basic point is that an orbital-polarized state with a spatially anisotropic overlap seems to enhance the charge ordering as we see below. To gain the kinetic energy in such a state at finite U and $\delta = 0.5$, an occupied site favors a vacant site as the nearest neighbors. In the model (1), the orbital polarization (OP) defined by $(\langle n_{x^2-y^2} \rangle - \langle n_{3z^2-r^2} \rangle) / (\langle n_{x^2-y^2} \rangle + \langle n_{3z^2-r^2} \rangle)$ grows because $d_{x^2-y^2}$ orbital has larger hopping matrix than $d_{3z^2-r^2}$ orbital. The strong interaction also enhances the polarization.¹⁷⁾ Actually the OP is ~ 0.756 at $\delta = 0.5$ for $U/t_0 = 16$ ²⁴⁾ in the 4×4 -site system. Note here that, on the other hand, the usual Hubbard model does not show such a spin polarization in the ground state at $\delta = 0.5$. When one uses $|\theta\rangle = \cos\theta|d_{x^2-y^2}\rangle + \sin\theta|d_{3z^2-r^2}\rangle$ as a notation for a single-site state, the above polarization leads to $|\theta|/\pi \simeq 0.114$, where each occupied orbital is strongly anisotropic and has a large overlap only in the x - or y -direction. We have next calculated the charge density correlation defined as $\Delta(\mathbf{k}) = N_s^{-1} \sum_{i,j} [\langle n_i n_j \rangle - \langle n_i \rangle \langle n_j \rangle] \exp[i\mathbf{k} \cdot (\mathbf{x}_i - \mathbf{x}_j)]$ in the 4×4 sites, where $n_i \equiv n_{i1} + n_{i2}$. The results at $\delta = 0.5$ show a peak at $\mathbf{k} = (\pi, \pi)$ which makes staggered charge correlation (CC). The doping dependence of the above CC at (π, π) is shown in Fig. 3. An anomalous peak appears at $\delta = 0.5$ only for the model (1) while the usual Hubbard model exhibits a monotonic δ dependence. A similar behavior at $\delta = 0.5$ of the CC and the charge dynamics was reported in ref. 28, where a spinless and orbitless system with the usual Hubbard-type hoppings and the nearest-neighbor interaction V was studied. Although the size treated here is too small to judge whether the present system is metallic or insulating, an anomalous behavior of $\Delta(\pi, \pi)$ at $\delta = 0.5$ occurs even in the present case without V . The enhanced CC at $\delta = 0.5$ which makes the suppressed coherence in the charge dynamics can be induced only by the anisotropic hopping and the on-site interaction while the static charge order will be more stabilized with the help of the inter-site Coulomb repulsion V . The JT distortion, studied theoretically by means of LDA+ U ²⁹⁾ and Hartree-Fock³⁰⁾ methods, will also enhance the above tendency of the CC and the incoherence of the charge dynamics. Although three dimensionality would reduce the OP, which influences the stability of this staggered CC, our results in 2D system are important because the charge-ordering phenomena essentially appear with strong 2D anisotropy in experiments.^{25, 26, 27, 31)} To obtain information of orbital patterns at $\delta = 0.5$, in addition, we calculate orbital correlations defined by $C \equiv \sum_{ij}' \langle W_i W_j \rangle$, where W_i denotes a pseudo-spin operator of $3x^2 - r^2$ or $3y^2 - r^2$ ($W_i \equiv -\frac{1}{2}T_i^z + (-)\frac{\sqrt{3}}{2}T_i^x$ for $3x^2(y^2) - r^2$, and $T_i^\mu = \frac{1}{2} \sum_{\nu\nu'} \hat{\sigma}_{\nu\nu'}^\mu c_{i\nu}^\dagger c_{i\nu'}$ with the Pauli matrix $\hat{\sigma}_{\nu\nu'}^\mu$). Prime at the sum means that i and j run over one sublattice. The possible patterns on the lattice are illustrated in Fig. 3. The results reveal that C for (a) is the largest.³²⁾ The pattern (a) agrees with the experimental indication.²⁶⁾ Thus, the basic orbital structure in charge-ordering phenomena is determined irrespective of magnetic structure due to difference of energy scales.

This situation is captured well within the model (1) in which the spin degrees of freedom are frozen out.

Finally, it is worth mentioning effects of the three dimensionality neglected above. In 2D, there happens the imbalance of populations in $d_{x^2-y^2}$ and $d_{3z^2-r^2}$ as described above. In 3D case, a hopping along z -axis would reduce the imbalance. We note that, in the NI case, such a reduction of OP in 3D from that in 2D decreases the coherence as inferred from the comparison between 3D case in ref. 10 and 2D one in Fig. 1. This is simply because the charge incoherence can not be induced if the orbital is completely polarized. The orbital depolarization may also be simulated by introducing a chemical potential difference between the two orbitals to compensate the existing OP. We have performed calculations for the $\sqrt{10} \times \sqrt{10}$ -site 2D Hamiltonian with such a chemical potential difference. The results show that the Drude weight becomes more suppressed. For example, if the chemical potential difference is tuned to keep the vanishing OP, $\frac{D}{N_{\text{eff}}} \sim 0.45$ at $\delta = 0.2$ as compared to $\frac{D}{N_{\text{eff}}} \sim 0.67$ in the case of Fig. 1. The broad shape of incoherence within the LH band near the Mott transition is found to be qualitatively unchanged after the chemical potential is introduced. These suggest the possibility that the depolarization due to the three dimensionality would also make the charge transport more incoherent.

In summary, we have investigated the optical conductivity $\sigma(\omega)$ of the double-exchange model with both the e_g -orbital degeneracy and the Coulomb interaction. Assuming the spin polarization and the strong Hund's-rule coupling in the 2D system, we have examined the effects of the orbital degeneracy and the on-site interaction. We have obtained in $\sigma(\omega)$ a suppressed Drude weight and a mid-gap incoherence with a broad structure in the metallic state near the Mott transition. The results reproduce to a considerable extent the incoherent charge dynamics observed experimentally in Mn oxides. On a quantitative level, however, the calculated Drude weight does not appear to be sufficiently small.^{7, 8)} Effects of fluctuations of JT distortion would be an additional source of the incoherence, which is an interesting subject of further studies for more quantitative comparison. We have also found an anomalous feature in charge transport and the charge correlation at quarter filling, which reproduces basic structure of the orbital and charge ordering observed in experiments.

The authors thank T. Ogitsu and S. Todo for useful advice to develop parallel-processing programs. Y.M. is supported by Research Fellowships of Japan Society for the Promotion of Science (JSPS) for Young Scientists. This work is supported by 'Research for the Future Program' from JSPS (JSPS-RFTF 97P01103). A part of the computations was performed using the facilities of the Supercomputer Center, Institute for Solid State Physics (ISSP), University of Tokyo. Parallel calculations were done in the supercomputer FUJITSU VPP500 in ISSP as well as in the VPP700 in Kyushu University.

[1] A. P. Ramirez: J. Phys. Condens. Matter **9** (1997) 8171 and references therein.

- [2] C. Zener: Phys. Rev. **82** (1951) 403.
- [3] P. W. Anderson and H. Hasegawa: Phys. Rev. **100** (1955) 675.
- [4] P. G. de Gennes: Phys. Rev. **118** (1960) 141.
- [5] K. Kubo and N. Ohata: J. Phys. Soc. Jpn. **33** (1972) 21.
- [6] N. Furukawa: J. Phys. Soc. Jpn. **63** (1995) 3214.
- [7] Y. Okimoto, T. Katsufuji, T. Ishikawa, A. Urushibara, T. Arima and Y. Tokura: Phys. Rev. Lett. **75** (1995) 109.
- [8] Y. Okimoto, T. Katsufuji, T. Ishikawa, T. Arima and Y. Tokura: Phys. Rev. B **55** (1997) 4206.
- [9] A. J. Millis, R. Mueller and B. I. Shraiman: Phys. Rev. B **54** (1996) 5405.
- [10] H. Shiba, R. Shiina and A. Takahashi: J. Phys. Soc. Jpn. **66** (1997) 941.
- [11] A. Takahashi and H. Shiba: Euro. Phys. J. B **5** (1998) 413.
- [12] P. E. de Brito and H. Shiba: Phys. Rev. B **57** (1998) 1539.
- [13] S. Ishihara, M. Yamanaka and N. Nagaosa: Phys. Rev. B **56** (1997) 686.
- [14] P. Horsch, J. Jaklic and F. Mack: Phys. Rev. B **59** (1999) 6217.
- [15] B.F. Woodfield, M.L. Wilson and J.M. Byes: Phys. Rev. Lett. **78** (1997) 3201.
- [16] In ref.14, the authors presented their data only above the temperature of $T = 0.3t_0$, where t_0 is a hopping amplitude which the authors themselves estimated to be 0.2 eV.
- [17] Y. Motome and M. Imada: J. Phys. Soc. Jpn. **68** (1999) 16.
- [18] T. Ishikawa, T. Kimura, T. Katsufuji and Y. Tokura: Phys. Rev. B **57** (1998) R8079.
- [19] Y. Motome, H. Nakano and M. Imada: preprint cond-mat/9811221.
- [20] Y. Motome and M. Imada: preprint cond-mat/9903183.
- [21] E. Gagliano and C. Balseiro: Phys. Rev. Lett. **59** (1987) 2999.
- [22] H. Nakano and M. Imada: J. Phys. Soc. Jpn. **68** (1999) 1458.
- [23] At this filling, the optimized boundary of 4×4 -site cluster at $U/t_0 = 16$ is a mixed one.
- [24] For comparison, the corresponding quantity for the non-interacting case is 0.25.
- [25] H. Kuwahara, Y. Tomioka, A. Asamitsu, Y. Moritomo and Y. Tokura: Science **270** (1995) 961.
- [26] Z. Jirak, S. Krupicka, Z. Simsa, M. Dlouha and S. Vratislav: J. Magn. Magn. Mater. **53** (1985) 153.
- [27] Y. Tomioka, A. Asamitsu, Y. Moritomo, H. Kuwahara and Y. Tokura: Phys. Rev. Lett. **74** (1995) 5108.
- [28] S. Ishihara and N. Nagaosa: J. Phys. Soc. Jpn. **66** (1997) 3678.
- [29] V. I. Anisimov, I. S. Elfimov and K. Terakura: Phys. Rev. B **55** (1997) 15494.
- [30] T. Mizokawa and A. Fujimori: Phys. Rev. B **56** (1997) R493.
- [31] Y. Murakami, H. Kawada, H. Kawata, M. Tanaka, T. Arima, Y. Moritomo and Y. Tokura: Phys. Rev. Lett. **80** (1998) 1932.
- [32] $C \sim 1.67$ for (a), ~ 1.41 for (b), ~ 1.29 for (c) of $3x^2 - r^2$ and ~ 1.49 for (c) of $3y^2 - r^2$ when the mixed BC is of $\Phi = (\pi, 0)$.

Fig. 1. Doping dependences of (a) the total weight K , (b) the effective carrier density N_{eff} and the Drude weight D at $U/t_0=16$. For comparison, gray lines show results in the non-interacting case, where the total weight, the effective carrier density and the Drude weight in the thermodynamic limit $N_s \rightarrow \infty$ are shown by the dotted line in (a), dotted one in (b) and solid one in (b), respectively.

Fig. 2. Incoherent part of the optical conductivity at $U/t_0 = 16$ for (a) the half-filled case in the 10-site system under the anti-periodic BC, (b) 2 holes in the 4×4 sites under the mixed BC, (c) 4 holes in the 4×4 sites under the anti-periodic BC. Inset in (b) shows the non-interacting case at the same filling and the same BC. Delta functions are broadened with width of $0.05t_0$. We choose the BC to realize the lowest-energy ground state.

Fig. 3. Doping dependences of the charge correlation. An anomaly at $\delta=0.5$ for the model (1) is obtained while only the monotonic behavior is seen in the usual Hubbard model. Insets (a), (b) and (c) display possible staggered patterns of orbitals at $\delta=0.5$ in 4×4 cluster. Simple circles and anisotropic symbols denote Mn^{4+} and Mn^{3+} with $3x^2 - r^2/3y^2 - r^2$, respectively.





